

frontier gray

testing data

ASTM C97	Water Absorption	.34%
ASTM C97	Bulk Specific Gravity	2.67
ASTM C170	Compressive Strength w/ Rift	19,034 psi
	Compressive Strength Across Rift	19,528 psi
ASTM C880	Flexural Strength w/ Rift	1,183 psi
	Flexural Strength Across Rift	1,160 psi

Tested on
November 12, 2002



Natural Stone

800.236.4473
www.buechelstone.com