

# indiana limestone

testing data

ASTM C97	Water Absorption	7.5%
ASTM C97	Bulk Specific Gravity	2.6 - 2.75
ASTM C99	Modulus of Rupture	700 psi
ASTM C170	Compressive Strength	4,000 psi



Natural Stone

800.236.4473

[www.buechelstone.com](http://www.buechelstone.com)