

silverdale

testing data

ASTM C97	Water Absorption	7.27%
ASTM C97	Density	134.1 pcf
ASTM C97	Specific Gravity	2.149
ASTM C99	Modulus of Rupture	1,174 psi
ASTM C170	Compressive Strength	6,631 psi
ASTM C241	Abrasion Resistance	5.38

Tested on
December 17, 2004



Natural Stone

800.236.4473
www.buechelstone.com