

St. Croix

testing data

ASTM C97	Water Absorption	3.5%
ASTM C99	Modulus of Rupture	1,200 psi
ASTM C170	Compressive Strength w/Rift	10,100 psi
	Compressive Strength Across Rift	9,650 psi
ASTM C880	Flexural Strength	820 psi

Tested on
April 27, 2011



Natural Stone

800.236.4473
www.buechelstone.com