

texas cream

testing data

ASTM C97	Water Absorption	6.13%
ASTM C97	Density	136.8 pcf
ASTM C97	Specific Gravity	2.193
ASTM C99	Modulus of Rupture	824 psi
ASTM C170	Compressive Strength	6,560 psi



Natural Stone

800.236.4473

www.buechelstone.com