

whispering pines

testing data

ASTM C97	Water Absorption	.96%
ASTM C97	Specific Gravity	2.65
ASTM C99	Modulus of Rupture	4,550 psi
ASTM C170	Compressive Strength	11,630 psi
ASTM C880	Flexural Strength	2,120 psi

Tested on
January 30, 2006



Natural Stone

800.236.4473
www.buechelstone.com