

## LEDGESTONE

### CHILTON RUSTIC LEDGESTONE



**GEOLOGY:** dolomitic limestone

#### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

#### COLOR RANGE

brown, buff, orange,  
yellow, red, and rust

#### COLOR CONSISTENCY PER PALLET

somewhat consistent

#### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 170$   
= approx 170 pounds per cubic foot

#### PALLET

FULL VENEER: 4,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)



## FULL VENEER

### COMMON COVERAGE \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

### CHILTON RUSTIC LEDGESTONE

#### DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 4" to 16" (8")	l: 100 to 400 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3" to 5" (4")	w: 76 to 127 (101)

#### TYPICAL BLEND

up to 30 percent may be sawn top and  
bottom with a bedface face;  
face of stone cannot have a sawn finish

#### TYPICAL PIECE

ends random;  
natural cleft top and bottom;  
weatheredge and seamface face;  
sides natural split or seamface;  
back sawn; stone is linear

## PART NUMBERS

### FULL VENEER

part number: 1B8TBUE01033TN

### THIN VENEER

qty bx flat: 1B8TVBUE01034QB  
sm bx flat: 1B8TVBUE01034BX  
qty bx corner: 1B8TVBUE01535QB  
sm bx corner: 1B8TVBUE01535BX

## THIN VENEER

### COMMON COVERAGE PER BOX \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

### CHILTON RUSTIC LEDGESTONE

#### DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 4" to 16" (8")	l: 100 to 400 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3/4" to 1-1/4" (1")	w: 19 to 38 (25)

corner return 3" to 5" cr: 76 to 127

#### TYPICAL BLEND

up to 30 percent may be sawn top and  
bottom with a bedface face;  
face of stone cannot have a sawn finish

#### TYPICAL PIECE

ends random;  
natural cleft top and bottom;  
weatheredge and seamface face;  
sides natural split or seamface;  
back sawn; stone is linear

## ASTM TESTING DATA

CHILTON C97 water absorption—0.08%  
CHILTON C97 density—177.4 pcf  
CHILTON C99 modulus of rupture—1,220 psi  
CHILTON C170  
compressive strength w/rift—50,560 psi  
compressive strength across rift—38,090 psi  
CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com