



## DIMENSIONAL

### CHILTON COLONIAL PAVERS

**GEOLOGY:** dolomitic limestone

#### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

#### COLOR RANGE

purple, lavender, mauve, gray,  
buff, blue, and brown;  
white from tumbling

#### COLOR CONSISTENCY PER PALLET

somewhat consistent

#### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 170$   
= approx 170 pounds per cubic foot

#### PALLET

FULL VENEER: 4,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

### FULL VENEER

#### COMMON COVERAGE \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

#### CHILTON COLONIAL PAVERS

##### DIMENSIONS

<b>US: inches</b>	<b>METRIC: mm</b>
l: 5" or 10"	l: 127 or 254
h: 5"	h: 127
w: 3" to 5"	w: 76 to 127

note:  $\pm 1/8$ " on sawn heights

##### TYPICAL PIECE

ends square;  
sawn top and bottom;  
sides are split;  
bedface face and back;  
back may be sawn;  
stone rounded from tumbling

### PART NUMBERS

#### FULL VENEER

part number 5"x 5"x 4": 1PAVBUE01007TN  
part number 5"x 5"x 5": 1PAVBUE01009TN  
part number 5"x 10"x 4": 1PAVBUE01008TN  
part number 5"x 10"x 5": 1PAVBUE01010TN

#### THIN VENEER

qty bx flat: 1BTVBUE01038QB  
sm bx flat: 1BTVBUE01038BX  
qty bx corner: 1BTVBUE01528QB  
sm bx corner: 1BTVBUE01528BX

### THIN VENEER

#### COMMON COVERAGE PER BOX \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

#### CHILTON COLONIAL PAVERS

##### DIMENSIONS

<b>US: inches (average)</b>	<b>METRIC: mm (average)</b>
l: 5" or 10"	l: 127 or 254
h: 5"	h: 127
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127

note:  $\pm 1/8$ " on sawn heights

##### TYPICAL PIECE

ends square;  
sawn top and bottom;  
sides are split;  
bedface face and sawn back;  
stone rounded from tumbling

### ASTM TESTING DATA

CHILTON C97 water absorption—0.08%

CHILTON C97 density—177.4 pcf

CHILTON C99 modulus of rupture—1,220 psi

CHILTON C170

compressive strength w/rift—50,560 psi

compressive strength across rift—38,090 psi

CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com