



**MOSAIC**  
**SPLIT GRANITE**  
**FIELDSTONE**

**GEOLOGY:** granite

**BASIC USE**

exterior walls of buildings and fireplaces  
stone shall be mortared in

**COLOR RANGE**

red, pinks,  
black, and blues

**COLOR CONSISTENCY PER PALLET**

somewhat consistent

**WEIGHT CALCULATED IN INCHES**

l x w x h / 1728 (inches cubed) x 170  
= approx 170 pounds per cubic foot

**PALLET**

FULL VENEER: 4,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

**FULL VENEER**

**COMMON COVERAGE** \*Est.(can vary)

Standard Joint	Drystack	Overgrout
35 square feet / ton	25 ft <sup>2</sup> /ton	45 ft <sup>2</sup> /ton

**SPLIT GRANITE FIELDSTONE**

**DIMENSIONS**

<b>US: inches</b>	<b>METRIC: mm</b>
l: 3" to 18" dia.	l: 76 to 457 dia.
h: 3" to 18" dia.	h: 76 to 457 dia.
w: 3" to 6"	w: 76 to 127

note: lengths and heights are irregular shapes  
3 inches to 18 inches in diameter

**TYPICAL PIECE**

ends irregular;  
irregular shaped pieces with a split face;  
sides and back may be split or round;  
corner pieces must have a split face and  
one side split at a 90 degree corner for  
a jamb for corners and next to windows

**PART NUMBERS**

**FULL VENEER**

part number: 1BSTGRA02001TN  
part number corners: 1BSTGRA02501TN

**THIN VENEER**

qty bx flat: 1BTVGRA02001QB  
sm bx flat: 1BTVGRA02001BX  
qty bx corner: 1BTVGRA02501QB  
sm bx corner: 1BTVGRA02501BX

**THIN VENEER**

**COMMON COVERAGE PER BOX** \*Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft <sup>2</sup>	10 & 110 ft <sup>2</sup>

**SPLIT GRANITE FIELDSTONE**

**DIMENSIONS**

<b>US: inches (average)</b>	<b>METRIC: mm (average)</b>
l: 3" to 12" dia.	l: 76 to 304 dia.
h: 3" to 12" dia.	h: 76 to 304 dia.
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127  
note: lengths and heights are irregular shapes  
3 inches to 12 inches in diameter

**TYPICAL PIECE**

ends irregular;  
irregular shaped pieces with a split face;  
sides may be split or round; back is sawn;  
corner pieces must have a split face and  
one side split at a 90 degree corner

**ASTM TESTING DATA**

SPLIT GRANITE FIELDSTONE C97  
water absorption—0.15%  
SPLIT GRANITE FIELDSTONE C97  
density—163.34 pcf  
SPLIT GRANITE FIELDSTONE C97  
specific gravity—2.6 to 2.81  
SPLIT GRANITE FIELDSTONE C170  
compressive strength—20,731 psi  
SPLIT GRANITE FIELDSTONE C880  
flexural strength—1,681 psi  
SPLIT GRANITE FIELDSTONE C241  
abrasion resistance—80.46



www.buechelstone.com