



LEDGESTONE

**CHILTON
TAILORED
LEDGESTONE**

GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

gray, mauve, purple,
lavender, buff, blue, brown,
yellow, red, and rust

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

THIN VENEER

CHILTON TAILORED LEDGESTONE

TYPICAL BLEND

100 percent splitface face;

face of stone cannot have a sawn finish

TYPICAL PIECE

ends sawn random lengths; sawn top,
bottom, and sides; face is splitface; back
sawn; stone is linear squares and rectangles

PART NUMBERS

FULL VENEER

part number: N/A

THIN VENEER

qty bx flat: 1BTVBUE01068QB

sm bx flat: 1BTVBUE01068BX

qty bx corner: 1BTVBUE01568QB

sm bx corner: 1BTVBUE01568BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Figured for Drystack Joint Only

8 & 100 square feet

CHILTON TAILORED LEDGESTONE

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 4" to 16" (8") l: 100 to 400 (203)

h: 1"; h: 2"; h: 4" h: 25; h: 51; h: 102

w: 3/4" to 1-1/4" (1") w: 19 to 38 (25)

corner return N/A cr: N/A

CORNER INSTALLATION



ASTM TESTING DATA

CHILTON C97 water absorption—0.08%

CHILTON C97 density—177.4 pcf

CHILTON C99 modulus of rupture—1,220 psi

CHILTON C170

compressive strength w/rift—50,560 psi

compressive strength across rift—38,090 psi

CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com