

## LEDGESTONE

### FOND DU LAC TAILORED LEDGESTONE



**GEOLOGY:** dolomitic limestone

#### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

#### COLOR RANGE

gray, light gray,  
buff, and white

#### COLOR CONSISTENCY PER PALLET

somewhat consistent

#### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 170$   
= approx 170 pounds per cubic foot

#### PALLET

FULL VENEER: 4,000 pounds

THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

### THIN VENEER

#### FOND DU LAC TAILORED LEDGESTONE

##### TYPICAL BLEND

100 percent splitface face;  
face of stone cannot have a sawn finish

##### TYPICAL PIECE

ends sawn random lengths; sawn top,  
bottom, and sides; face is splitface; back  
sawn; stone is linear squares and rectangles



### PART NUMBERS

#### FULL VENEER

part number: N/A

#### THIN VENEER

qty bx flat: 1BTVBUE02068QB  
sm bx flat: 1BTVBUE02068BX  
qty bx corner: 1BTVBUE02568QB  
sm bx corner: 1BTVBUE02568BX

### THIN VENEER

#### COMMON COVERAGE PER BOX\*<sup>Est.(can vary)</sup>

Figured for Drystack Joint Only  
8 & 100 square feet

#### FOND DU LAC TAILORED LEDGESTONE

##### DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 4" to 16" (8") l: 100 to 400 (203)

h: 1"; h: 2"; h: 4" h: 25; h: 51; h: 102

w: 3/4" to 1-1/4" (1") w: 19 to 38 (25)

corner return N/A cr: N/A

##### CORNER INSTALLATION



### ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%

FOND DU LAC C97 density—174.2 pcf

FOND DU LAC C99

modulus of rupture—1,470 psi

FOND DU LAC C170

compressive strength w/rift—29,040 psi

compressive strength across rift—34,240 psi

FOND DU LAC C880

flexural strength—1,740 psi



www.buechelstone.com