



TAILORED FIELDLEDGE

BARNWOOD BLUE TAILORED FIELDLEDGE

GEOLOGY: schist

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

grays, dark grays, charcoals, whites, blues,
tans with occasional greens, buffs, and blacks

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: N/A (Natural Thin Veneer Only)
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER (N/A)

**BARNWOOD BLUE TAILORED FIELDLEDGE
NTV (NATURAL THIN VENEER) ONLY**
Barnwood Blue Tailored Fieldledge is a Thin
Veneer product only; so there is no applicable
Full Veneer spec information to report.
Please find detailed data for this Thin Veneer
product listed in the far right column.
Thank you.

PART NUMBERS

FULL VENEER
part number: N/A

THIN VENEER

qty bx flat: 1BTVGRA03061QB
sm bx flat: 1BTVGRA03061BX
qty bx corner: 1BTVGRA03561QB
sm bx corner: 1BTVGRA03561BX

ASTM TESTING DATA

BARNWOOD BLUE C97
water absorption—0.5%
BARNWOOD BLUE C97
specific gravity—2.75
BARNWOOD BLUE C97
density—171.8 pcf
BARNWOOD BLUE C99
modulus of rupture perpendicular
dry—3,490 psi
modulus of rupture perpendicular
wet—2,920 psi
BARNWOOD BLUE C170
compressive strength parallel dry—12,260 psi
compressive strength parallel wet—9,770 psi
compressive strength perpendicular
dry—15,300 psi
compressive strength perpendicular
wet—11,220 psi

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)
Figured for Drystacked Joint Only
8 & 100 square feet

BARNWOOD BLUE TAILORED FIELDLEDGE DIMENSIONS

US: inches (average) **METRIC: mm (average)**
l: 3" to 24" dia. l: 76 to 610 dia.
h: 2"; h: 4"; h: 6" h: 51; h: 102; h: 152
w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)
corner return N/A cr: N/A
note: sawn heights with varying lengths
having rough irregular ends

TYPICAL PIECE

ends irregular; random lengths;
sawn top and bottom; sides not square;
bedface face and sawn back;
overall appearance of stone will be linear
when installed

CORNER INSTALLATION

