



DIMENSIONAL

FOND DU LAC SHABBY-CHIC TAILORED BLEND

GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

light gray to white

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds

THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx

Qty Bx - 100 sq ft flats and 50 lineal ft corners

Sm Bx - (24) 8 sq ft flats (192 sq ft) and

(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE ^{*Est.(can vary)}

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

FOND DU LAC SHABBY-CHIC TAILORED BLEND

DIMENSIONS

US: inches (average)	METRIC: mm (average)
-----------------------------	-----------------------------

l: 6" to 24" (12")	l: 152 to 533 (304)
--------------------	---------------------

h: 2-1/4"; h: 5";	h: 57; h: 127;
-------------------	----------------

h: 7-3/4"	h: 196
-----------	--------

w: 3" to 5" (4")	w: 76 to 127 (101)
------------------	--------------------

note: ± 1/8" on sawn heights

TYPICAL BLEND

33.33 percent 2-1/4"; 33.33 percent 5";

33.33 percent 7-3/4"

TYPICAL PIECE

ends square; all sides sawn;

stone is rectangular having linear sawn

appearance with length longer than height

PART NUMBERS

FULL VENEER

part number: 1BSTBUE02070TN

THIN VENEER

qty bx flat: 1BTVBUE02070QB

sm bx flat: 1BTVBUE02070BX

qty bx corner: 1BTVBUE02570QB

sm bx corner: 1BTVBUE02570BX

THIN VENEER

COMMON COVERAGE PER BOX ^{*Est.(can vary)}

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

FOND DU LAC SHABBY-CHIC TAILORED BLEND

DIMENSIONS

US: inches (average)	METRIC: mm (average)
-----------------------------	-----------------------------

l: 6" to 24" (12")	l: 152 to 533 (304)
--------------------	---------------------

h: 2-1/4"; h: 5";	h: 57; h: 127;
-------------------	----------------

h: 7-3/4"	h: 196
-----------	--------

w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)
------------------------	------------------

corner return 3" to 5" cr: 76 to 127

note: ± 1/8" on sawn heights

TYPICAL BLEND

33.33 percent 2-1/4"; 33.33 percent 5";

33.33 percent 7-3/4"

TYPICAL PIECE

ends square; all sides sawn;

stone is rectangular having linear sawn

appearance with length longer than height

ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%

FOND DU LAC C97 density—174.2 pcf

FOND DU LAC C99

modulus of rupture—1,470 psi

FOND DU LAC C170

compressive strength w/rift—29,040 psi

compressive strength across rift—34,240 psi

FOND DU LAC C880

flexural strength—1,740 psi

