

LEDGESTONE

CHILTON RUSTIC LEDGESTONE



GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

brown, buff, orange,
yellow, red, and rust

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)



FULL VENEER

COMMON COVERAGE ^{*Est.(can vary)}

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

CHILTON RUSTIC LEDGESTONE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 4" to 16" (8")	l: 102 to 406 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3" to 5" (4")	w: 76 to 127 (101)

TYPICAL BLEND

up to 30 percent may be sawn top and
bottom with a bedface face;
face of stone cannot have a sawn finish

TYPICAL PIECE

ends random;
natural cleft top and bottom;
weatheredge and seamface face;
sides natural split or seamface;
back sawn; stone is linear

PART NUMBERS

FULL VENEER

part number: 1BSTBUE01033TN

THIN VENEER

qty bx flat: 1BTVBUE01034QB
sm bx flat: 1BTVBUE01034BX
qty bx corner: 1BTVBUE01535QB
sm bx corner: 1BTVBUE01535BX

THIN VENEER

COMMON COVERAGE PER BOX ^{*Est.(can vary)}

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

CHILTON RUSTIC LEDGESTONE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 4" to 16" (8")	l: 102 to 406 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3/4" to 1-1/4" (1")	w: 19 to 38 (25)

corner return 3" to 5" cr: 76 to 127

TYPICAL BLEND

up to 30 percent may be sawn top and
bottom with a bedface face;
face of stone cannot have a sawn finish

TYPICAL PIECE

ends random;
natural cleft top and bottom;
weatheredge and seamface face;
sides natural split or seamface;
back sawn; stone is linear

ASTM TESTING DATA

CHILTON C97 water absorption—0.08%
CHILTON C97 density—177.4 pcf
CHILTON C99 modulus of rupture—1,220 psi
CHILTON C170
compressive strength w/rift—50,560 psi
compressive strength across rift—38,090 psi
CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com