



## PATIO & PAVING

### FOND DU LAC STEPPERS

**GEOLOGY:** dolomitic limestone

#### BASIC USE

on patios and walkways; stone is dryset in gravel (screenings) bed or mortared in

#### COLOR RANGE

gray, light gray, buff, and white

#### COLOR CONSISTENCY PER PALLET

somewhat consistent

#### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed) x 170  
= approx 170 pounds per cubic foot

#### PALLET

4,000 pounds

## PATIO & PAVING

### COMMON COVERAGE <sup>\*Est.(can vary)</sup>

1" to 2" height      1-3/4" to 2-1/2"  
80 square feet / ton      65 ft<sup>2</sup>/ton

### FOND DU LAC STEPPERS

#### DIMENSIONS

##### US: inches

l: 8" to 24"

h: 1" to 2" or

h: 1-3/4" to 2-1/2"

w: 8" to 24"

note: lengths and widths are irregular shapes

8 inches to 24 inches in diameter

##### METRIC: mm

l: 203 to 609 mm

h: 25 to 51 mm or

h: 44 to 63 mm

w: 203 to 609 mm

## PART NUMBERS

part no. 1" to 2": 1PATBUE02015TN

part no. 1-3/4" to 2-1/2": 1PATBUE02017TN

## PATIO & PAVING

### FOND DU LAC STEPPERS

#### TYPICAL PIECE

ends irregular;

natural cleft top and bottom;

natural split sides;

stone is random shapes

## ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%

FOND DU LAC C97 density—174.2 pcf

FOND DU LAC C99

modulus of rupture—1,470 psi

FOND DU LAC C170

compressive strength w/rift—29,040 psi

compressive strength across rift—34,240 psi

FOND DU LAC C880

flexural strength—1,740 psi



www.buechelstone.com