

STEPS

MILL CREEK SNAPPED STEPS



GEOLOGY: dolomitic limestone

BASIC USE

for steps

COLOR RANGE

top or bottom buff to brown;
face and sides light gray to buff
with occasional blue veins

COLOR CONSISTENCY PER PALLET

consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

4,000 pounds

STEPS PER PALLET

18" x 36" = 8 steps per pallet
24" x 36" = 5 steps per pallet
18" x 48" = 6 steps per pallet
24" x 48" = 5 steps per pallet
18" x 60" = 5 steps per pallet



SNAPPED STEPS

COVERAGES

coverages calculated as specified per project

MILL CREEK 18"x36" SNAPPED STEPS

DIMENSIONS

US: inches	METRIC: mm
l: 35" to 37"	l: 889 to 939 mm
h: 5" to 8"	h: 127 to 203 mm
w: 17" to 19"	w: 431 to 482 mm

note: $\pm 2"$ on split lengths and widths

note: $\pm 3"$ on natural cleft height

MILL CREEK 24"x36" SNAPPED STEPS

DIMENSIONS

US: inches	METRIC: mm
l: 35" to 37"	l: 889 to 939 mm
h: 5" to 8"	h: 127 to 203 mm
w: 23" to 25"	w: 584 to 635 mm

note: $\pm 2"$ on split lengths and widths

note: $\pm 3"$ on natural cleft height

MILL CREEK 18"x48" SNAPPED STEPS

DIMENSIONS

US: inches	METRIC: mm
l: 47" to 49"	l: 1193 to 1244 mm
h: 5" to 8"	h: 127 to 203 mm
w: 17" to 19"	w: 431 to 482 mm

note: $\pm 2"$ on split lengths and widths

note: $\pm 3"$ on natural cleft height

PART NUMBERS

part number 18"x36": 1STELEN01002EA

part number 24"x36": 1STELEN01004EA

part number 18"x48": 1STELEN01001EA

part number 24"x48": 1STELEN01006EA

part number 18"x60": 1STELEN01007EA

SNAPPED STEPS

MILL CREEK 24"x48" SNAPPED STEPS

DIMENSIONS

US: inches	METRIC: mm
l: 47" to 49"	l: 1193 to 1244 mm
h: 5" to 8"	h: 127 to 203 mm
w: 23" to 25"	w: 584 to 635 mm

note: $\pm 2"$ on split lengths and widths

note: $\pm 3"$ on natural cleft height

MILL CREEK 18"x60" SNAPPED STEPS

DIMENSIONS

US: inches	METRIC: mm
l: 59" to 61"	l: 1499 to 1549 mm
h: 5" to 8"	h: 127 to 203 mm
w: 17" to 19"	w: 431 to 482 mm

note: $\pm 2"$ on split lengths and widths

note: $\pm 3"$ on natural cleft height

TYPICAL PIECE

ends square;

natural cleft top and bottom;

split sides, face and back;

stone is rectangular;

custom sizing by request

ASTM TESTING DATA

MILL CREEK C97 water absorption—0.66%

MILL CREEK C97 density—173.0 pcf

MILL CREEK C99

modulus of rupture—2,072 psi

MILL CREEK C170

compressive strength—26,260 psi

MILL CREEK C880 flexural strength—1,374 psi



www.buechelstone.com