

MILL CREEK

testing data

Stone Type:	Dolomitic Limestone	
ASTM C97	Water Absorption	.66%
ASTM C97	Density	173 pcf
ASTM C97	Bulk Specific Gravity	2.77
ASTM C99	Modulus of Rupture	2,072 psi
ASTM C170	Compressive Strength	26,260 psi
ASTM C880	Flexural Strength	1,374 psi
ASTM C482	Shear Bond Strength	314 psi



Natural Stone

800.236.4473
www.buechelstone.com