MOSAIC

ANTIQUE COPPER FIELDSTONE

GEOLOGY: sandstone

BASIC USE
exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE
burnt tones, browns, buffs, black, red, mustard, occasional moss and lichens

COLOR CONSISTENCY PER PALLET
somewhat consistent

WEIGHT CALCULATED IN INCHES
l x w x h / 1728 (inches cubed) x 165
= approx 165 pounds per cubic foot

PALLET
FULL VENEER: 3,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
35 square feet / ton	25 ft²/ton	45 ft²/ton

ANTIQUE COPPER FIELDSTONE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 3" to 16" dia.	l: 76 to 406 dia.
h: 3" to 16" dia.	h: 76 to 406 dia.
w: 3" to 6" (4")	w: 76 to 152 (101)

note: lengths and heights are irregular shapes
3 inches to 16 inches in diameter

TYPICAL PIECE

ends irregular;
natural split and rounded sides;
bedface face and back;
stone is random shapes

PART NUMBERS

FULL VENEER
part number: 1BSTSCH01002TN

THIN VENEER
qty bx flat: 1BTVSCH01001QB
sm bx flat: 1BTVSCH01001BX
qty bx corner: 1BTVSCH01501QB
sm bx corner: 1BTVSCH01501BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft²	10 & 110 ft²

ANTIQUE COPPER FIELDSTONE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 3" to 12" dia.	l: 76 to 304 dia.
h: 3" to 12" dia.	h: 76 to 304 dia.
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)
corner return 3" to 5"	cr: 76 to 127

note: lengths and heights are irregular shapes
3 inches to 12 inches in diameter

TYPICAL PIECE

ends irregular;
natural split and rounded sides;
bedface face and sawn back;
stone is random shapes

ASTM TESTING DATA

ANTIQUE COPPER C97
water absorption—2.8%
ANTIQUE COPPER C97 density—149.3 pcf
ANTIQUE COPPER C97 specific gravity—2.393
ANTIQUE COPPER C1549-09
solar reflectance—24.7%
ANTIQUE COPPER C1371-15
thermal emittance—0.90
ANTIQUE COPPER E1980-11
solar reflective index—25