



MOSAIC
SPLIT GRANITE
FIELDSTONE

GEOLOGY: granite

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

red, pinks,
black, and blues

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
35 square feet / ton	25 ft ² /ton	45 ft ² /ton

SPLIT GRANITE FIELDSTONE

DIMENSIONS

US: inches	METRIC: mm
l: 3" to 18" dia.	l: 76 to 457 dia.
h: 3" to 18" dia.	h: 76 to 457 dia.
w: 3" to 6"	w: 76 to 127

note: lengths and heights are irregular shapes
3 inches to 18 inches in diameter

TYPICAL PIECE

ends irregular;
irregular shaped pieces with a split face;
sides and back may be split or round;
corner pieces must have a split face and
one side split at a 90 degree corner for
a jamb for corners and next to windows

PART NUMBERS

FULL VENEER

part number: 1BSTGRA02001TN
part number corners: 1BSTGRA02501TN

THIN VENEER

qty bx flat: 1BTVGRA02001QB
sm bx flat: 1BTVGRA02001BX
qty bx corner: 1BTVGRA02501QB
sm bx corner: 1BTVGRA02501BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

SPLIT GRANITE FIELDSTONE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 3" to 12" dia.	l: 76 to 304 dia.
h: 3" to 12" dia.	h: 76 to 304 dia.
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127
note: lengths and heights are irregular shapes
3 inches to 12 inches in diameter

TYPICAL PIECE

ends irregular;
irregular shaped pieces with a split face;
sides may be split or round; back is sawn;
corner pieces must have a split face and
one side split at a 90 degree corner

ASTM TESTING DATA

SPLIT GRANITE FIELDSTONE C97
water absorption—0.15%
SPLIT GRANITE FIELDSTONE C97
density—163.34 pcf
SPLIT GRANITE FIELDSTONE C97
specific gravity—2.6 to 2.81
SPLIT GRANITE FIELDSTONE C170
compressive strength—20,731 psi
SPLIT GRANITE FIELDSTONE C880
flexural strength—1,681 psi
SPLIT GRANITE FIELDSTONE C241
abrasion resistance—80.46



www.buechelstone.com