



FIELDLEDGE

**AUTUMN
SIENA**

GEOLOGY: quartzitic sandstone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

buff, gray to black, orange,
pink, and cream with swirls

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 160
= approx 160 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

AUTUMN SIENA

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 4" to 16" l: 101 to 406

h: 2" to 8" h: 50 to 203

w: 3" to 5" (4") w: 76 to 127 (101)

note: product can vary in height from full height to half the total height in one piece

TYPICAL BLEND

10 percent installed bedface out;
stone is snapped at least one face;
sides may or may not be squared;
overall appearance of stone will be linear when installed

TYPICAL PIECE

ends random;
natural cleft top and bottom;
split or natural split face, split back;
most sides more irregular and not square

PART NUMBERS

FULL VENEER

part number: 1BSTTEN01004TN

THIN VENEER

qty bx flat: 1BTVTEN01004QB

sm bx flat: 1BTVTEN01004BX

qty bx corner: 1BTVTEN01504QB

sm bx corner: 1BTVTEN01504BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

AUTUMN SIENA

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 4" to 16" l: 101 to 406

h: 2" to 8" h: 50 to 203

w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127

note: product can vary in height from full height to half the total height in one piece

TYPICAL BLEND

10 percent installed bedface out;
stone is snapped at least one face;
sides may or may not be squared;
overall appearance of stone will be linear when installed

TYPICAL PIECE

ends random;
natural cleft top and bottom;
split or natural split face and sawn back;
most sides more irregular and not square

ASTM TESTING DATA

AUTUMN SIENA C97

water absorption—1.92%

AUTUMN SIENA C97 density—156.0 pcf

AUTUMN SIENA C97

specific gravity—2.495

AUTUMN SIENA C170

compressive strength—16,550 psi

AUTUMN SIENA C880

flexural strength—1,580 psi



www.buechelstone.com