



FIELDLEDGE

**CHILTON
HERITAGE
BLEND**

GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

gray to charcoal with occasional mauves,
brown, buff, orange, yellow, red, rust, blue,
lavendar, purple, and charcoal

COLOR CONSISTENCY PER PALLET

inconsistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

CHILTON HERITAGE BLEND

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 6" to 24" l: 152 to 609

h: 2" to 12" h: 50 to 304

w: 3" to 5" (4") w: 76 to 127 (101)

note: lengths and heights can vary with
rough irregular shapes mixed in

TYPICAL PIECE

ends random;

completely random mix of Chilton material;

rough-cut stone is a mixture of splitface,
natural splitface, and bedface;

stone is mixture of square, rectangular,
triangular, trapezoidal, and parallelogram
shapes

PART NUMBERS

FULL VENEER

part number: 1BSTBUE01017TN

THIN VENEER

qty bx flat: 1BTVBUE01016QB

sm bx flat: 1BTVBUE01016BX

qty bx corner: 1BTVBUE01516QB

sm bx corner: 1BTVBUE01516BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

CHILTON HERITAGE BLEND

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 6" to 24" l: 152 to 609

h: 2" to 12" h: 50 to 304

w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127

note: lengths and heights can vary with
rough irregular shapes mixed in

TYPICAL PIECE

ends random;

completely random mix of Chilton material;

rough-cut stone is a mixture of splitface,
natural splitface, and bedface;

stone is mixture of square, rectangular,
triangular, trapezoidal, and parallelogram
shapes; back of stone is sawn

ASTM TESTING DATA

CHILTON C97 water absorption—0.08%

CHILTON C97 density—177.4 pcf

CHILTON C99 modulus of rupture—1,220 psi

CHILTON C170

compressive strength w/rift—50,560 psi

compressive strength across rift—38,090 psi

CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com