



DIMENSIONAL

CHILTON SHABBY-CHIC TAILORED BLEND

GEOLOGY: dolomitic limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

gray to charcoal,
with occasional mauves

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

CHILTON SHABBY-CHIC TAILORED BLEND

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 6" to 24" (12") l: 152 to 533 (304)

h: 2-1/4"; h: 5"; h: 57; h: 127;

h: 7-3/4" h: 196

w: 3" to 5" (4") w: 76 to 127 (101)

note: $\pm 1/8$ " on sawn heights

TYPICAL BLEND

33.33 percent 2-1/4"; 33.33 percent 5";

33.33 percent 7-3/4"

TYPICAL PIECE

ends square; all sides sawn;

stone is rectangular having linear sawn

appearance with length longer than height

PART NUMBERS

FULL VENEER

part number: 1BSTBUE01070TN

THIN VENEER

qty bx flat: 1BTVBUE01070QB

sm bx flat: 1BTVBUE01070BX

qty bx corner: 1BTVBUE01750QB

sm bx corner: 1BTVBUE01750BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

CHILTON SHABBY-CHIC TAILORED BLEND

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 6" to 24" (12") l: 152 to 533 (304)

h: 2-1/4"; h: 5"; h: 57; h: 127;

h: 7-3/4" h: 196

w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127

note: $\pm 1/8$ " on sawn heights

TYPICAL BLEND

33.33 percent 2-1/4"; 33.33 percent 5";

33.33 percent 7-3/4"

TYPICAL PIECE

ends square; all sides sawn;

stone is rectangular having linear sawn

appearance with length longer than height

ASTM TESTING DATA

CHILTON C97 water absorption—0.08%

CHILTON C97 density—177.4 pcf

CHILTON C99 modulus of rupture—1,220 psi

CHILTON C170

compressive strength w/rift—50,560 psi

compressive strength across rift—38,090 psi

CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com