LEDGESTONE

CHILTON TAILORED LEDGESTONE

GEOLOGY: dolomitic limestone

BASIC USE
exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE
gray, mauve, purple,
lavender, buff, blue, brown,
yellow, red, and rust

COLOR CONSISTENCY PER PALLET
somewhat consistent

WEIGHT CALCULATED IN INCHES
l x w x h / 1728 (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET
FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft^2; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

THIN VENEER

CHILTON TAILORED LEDGESTONE

TYPICAL BLEND
100 percent splitface face;
face of stone cannot have a sawn finish

TYPICAL PIECE
ends sawn random lengths; sawn top, bottom, and sides; face is splitface; back sawn; stone is linear squares and rectangles

PART NUMBERS

FULL VENEER
part number: N/A

THIN VENEER
qty bx flat: 1BTVBUE01068QB
sm bx flat: 1BTVBUE01068BX
qty bx corner: 1BTVBUE01568QB
sm bx corner: 1BTVBUE01568BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)
Figured for Drystacked Joint Only
8 & 100 square feet

CHILTON TAILORED LEDGESTONE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 4" to 16" (8")	l: 102 to 406 (203)
h: 1"; h: 2"; h: 4"	h: 25; h: 51; h: 102
w: 3/4" to 1-1/4" (1")	w: 19 to 38 (25)
corner return N/A	cr: N/A

CORNER INSTALLATION

ASTM TESTING DATA

CHILTON C97 water absorption—0.08%
CHILTON C97 density—177.4 pcf
CHILTON C99 modulus of rupture—1,220 psi
CHILTON C170
compressive strength w/rift—50,560 psi
compressive strength across rift—38,090 psi
CHILTON C880 flexural strength—3,070 psi