

ASHLAR

TENNESSEE SPLITFACE



GEOLOGY: quartzitic sandstone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

orange, pink, and
cream with swirls

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 165
= approx 165 pounds per cubic foot

PALLET

FULL VENEER: 3,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE ^{*Est.(can vary)}

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

TENNESSEE SPLITFACE

DIMENSIONS

US: inches	METRIC: mm
l: 6" to 42"	l: 152 to 1066
h: 1/2" to 8"	h: 13 to 203
w: 3" to 5"	w: 76 to 127

TYPICAL PIECE

ends square;
natural cleft top and bottom;
back, face, and sides split;
stone is mostly rectangular

PART NUMBERS

FULL VENEER

part number: 1BSTTEN01001TN

THIN VENEER

qty bx flat: 1BTVTEN01001QB
sm bx flat: 1BTVTEN01001BX
qty bx corner: 1BTVTEN01501QB
sm bx corner: 1BTVTEN01501BX

THIN VENEER

COMMON COVERAGE PER BOX ^{*Est.(can vary)}

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

TENNESSEE SPLITFACE

DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 6" to 42"	l: 152 to 1066
h: 1/2" to 8"	h: 13 to 203
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)

TYPICAL PIECE

ends square;
natural cleft top and bottom;
face and sides split; sawn back;
stone is mostly rectangular

ASTM TESTING DATA

TENNESSEE C97 water absorption—1.92%
TENNESSEE C97 density—156.0 pcf
TENNESSEE C97
specific gravity—2.495
TENNESSEE C170
compressive strength—16,550 psi
TENNESSEE C880 flexural strength—1,580 psi



www.buechelstone.com