

CASTLE ROCK

ANTIQUE BLACK
CASTLE ROCK



GEOLOGY: quartzitic sandstone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

blacks, charcoals, grays, rust, bronze, brown
and whites, with occasional blues and greens

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$I \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint Drystack Overgrout
35 square feet / ton 25 ft²/ton 45 ft²/ton

ANTIQUE BLACK CASTLE ROCK

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 4" to 24" (14") l: 101 to 609 (355)

h: 4" to 12" h: 101 to 305

w: 3" to 5" (4") w: 76 to 127 (101)

stone shall not vary in height more than 1/2
an inch in a 12 inch span

TYPICAL PIECE

ends somewhat square;
split or natural split top, bottom, and sides;
bedface face and back; stone is squares and
rectangles



PART NUMBERS

FULL VENEER

part number: 1BSTGRA04007TN

THIN VENEER

qty bx flat: 1BTVGRA03026BX

sm bx flat: 1BTVGRA03026QB

qty bx corner: 1BTVGRA03526QB

sm bx corner: 1BVGRA03526BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint Drystack Overgrout
8 & 100 square feet 6 & 75 ft² 10 & 110 ft²

ANTIQUE BLACK CASTLE ROCK

DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 4" to 24" (14") l: 101 to 609 (355)

h: 4" to 12" h: 101 to 305

w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)

corner return 3" to 6" cr: 76 to 152

TYPICAL PIECE

ends somewhat square;
split or natural split top, bottom, and sides;
bedface face and sawn back; stone is squares and
rectangles

ASTM TESTING DATA

ANTIQUE BLACK C97

water absorption—0.2%

ANTIQUE BLACK C97

specific gravity—3.051

ANTIQUE BLACK C97

density—190.4pcf

ANTIQUE BLACK C99

modulus of rupture dry—3,040 psi

modulus of rupture wet—2,610 psi

ANTIQUE BLACK C170

compressive strength parallel dry—15,070 psi

compressive strength parallel

wet—12,070 psi

compressive strength perpendicular

dry—25,340 psi

compressive strength perpendicular

wet—15,070 psi