



DIMENSIONAL
SILVERDALE
TAILORED BLEND

GEOLOGY: limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

buffs, tans and creams,
with occasional grays

COLOR CONSISTENCY PER PALLET

consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) x 160
= approx 160 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

SILVERDALE TAILORED BLEND

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 6" to 42" (24") l: 152 to 1066 (609)

h: 2-1/4"; h: 5"; h: 57; h: 127;

h: 7-3/4"; h: 10-1/2" h: 196; h: 266

w: 3" to 5" (4") w: 76 to 127 (101)

note: ± 1/8" on sawn heights

ADDITIONAL SIZES

other custom heights available:

TYPICAL BLEND

20 percent 2-1/4"; 40 percent 5";

30 percent 7-3/4"; 10 percent 10-1/2"

TYPICAL PIECE

ends square;

sawn top and bottom; sides are split;

splitface face and back with occasional bedface;

stone is rectangular in appearance with length longer than height

PART NUMBERS

FULL VENEER

part number: 1BSTKNS01001TN

THIN VENEER

qty bx flat: 1BTVKNS01001QB

sm bx flat: 1BTVKNS01001BX

qty bx corner: 1BTVKNS01501QB

sm bx corner: 1BTVKNS01501BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

SILVERDALE TAILORED BLEND

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 6" to 24" (12") l: 152 to 533 (304)

h: 2-1/4"; h: 5"; h: 57; h: 127;

h: 7-3/4"; h: 10-1/2" h: 196; h: 266

w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127

note: ± 1/8" on sawn heights

ADDITIONAL SIZES

other custom heights available:

TYPICAL BLEND

20 percent 2-1/4"; 40 percent 5";

30 percent 7-3/4"; 10 percent 10-1/2"

TYPICAL PIECE

ends square;

sawn top and bottom; sides are split;

splitface face with occasional bedface and

sawn back;

stone is rectangular in appearance with length longer than height

ASTM TESTING DATA

SILVERDALE C97 water absorption—7.27%

SILVERDALE C97 density—134.1 pcf

SILVERDALE C97 specific gravity—2.149

SILVERDALE C99

modulus of rupture—1,174 psi

SILVERDALE C170

compressive strength—6,631 psi

SILVERDALE C241 abrasion resistance—5.38



www.buechelstone.com