



**LEDGESTONE**

**CHILTON  
RUSTIC  
LEDGESTONE**

**GEOLOGY:** dolomitic limestone

**BASIC USE**

exterior walls of buildings and fireplaces  
stone shall be mortared in

**COLOR RANGE**

brown, buff, orange,  
yellow, red, and rust

**COLOR CONSISTENCY PER PALLET**

somewhat consistent

**WEIGHT CALCULATED IN INCHES**

$l \times w \times h / 1728$  (inches cubed)  $\times 170$   
= approx 170 pounds per cubic foot

**PALLET**

FULL VENEER: 4,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)

**FULL VENEER**

**COMMON COVERAGE** \*Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

**CHILTON RUSTIC LEDGESTONE**

**DIMENSIONS**

**US: inches (average)**    **METRIC: mm (average)**

l: 4" to 16" (8")    l: 102 to 406 (203)

h: 3/4" to 2-1/4"    h: 19 to 57

w: 3" to 5" (4")    w: 76 to 127 (101)

**TYPICAL BLEND**

up to 30 percent may be sawn top and  
bottom with a bedface face;

face of stone cannot have a sawn finish

**TYPICAL PIECE**

ends random;

natural cleft top and bottom;

weatheredge and seamface face;

sides natural split or seamface;

back sawn; stone is linear

**PART NUMBERS**

**FULL VENEER**

part number: 1BSTBUE01033TN

**THIN VENEER**

qty bx flat: 1BTVBUE01034QB

sm bx flat: 1BTVBUE01034BX

qty bx corner: 1BTVBUE01535QB

sm bx corner: 1BTVBUE01535BX

**THIN VENEER**

**COMMON COVERAGE PER BOX** \*Est.(can vary)

Drystack Joint	Standard Joint
8 & 100 square feet	10 & 110 ft <sup>2</sup>

note: packaged for drystack install (8 & 100 ft<sup>2</sup>)

note: packaged for drystack install (8 & 100 ft<sup>2</sup>)

**CHILTON RUSTIC LEDGESTONE**

**DIMENSIONS**

**US: inches (average)**    **METRIC: mm (average)**

l: 4" to 16" (8")    l: 102 to 406 (203)

h: 3/4" to 2-1/4"    h: 19 to 57

w: 3/4" to 1-1/4" (1")    w: 19 to 38 (25)

corner return 3" to 5"    cr: 76 to 127

**TYPICAL BLEND**

up to 30 percent may be sawn top and  
bottom with a bedface face;

face of stone cannot have a sawn finish

**TYPICAL PIECE**

ends random;

natural cleft top and bottom;

weatheredge and seamface face;

sides natural split or seamface;

back sawn; stone is linear

**ASTM TESTING DATA**

CHILTON C97 water absorption—0.08%

CHILTON C97 density—177.4 pcf

CHILTON C99 modulus of rupture—1,220 psi

CHILTON C170

compressive strength w/rift—50,560 psi

compressive strength across rift—38,090 psi

CHILTON C880 flexural strength—3,070 psi



www.buechelstone.com