

# LEDGESTONE

FOND DU LAC  
RUSTIC  
LEDGESTONE



**GEOLOGY:** dolomitic limestone

### BASIC USE

exterior walls of buildings and fireplaces  
stone shall be mortared in

### COLOR RANGE

brown, buff, tan, and gold

### COLOR CONSISTENCY PER PALLET

consistent

### WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 170  
= approx 170 pounds per cubic foot

### PALLET

FULL VENEER: 3,000 pounds  
THIN VENEER: 10-15 lbs/ft<sup>2</sup>; Qty Bx or Sm Bx  
Qty Bx - 100 sq ft flats and 50 lineal ft corners  
Sm Bx - (24) 8 sq ft flats (192 sq ft) and  
(20) 8 lineal ft corners (160 lineal ft)



## FULL VENEER

### COMMON COVERAGE <sup>\*Est.(can vary)</sup>

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft <sup>2</sup> /ton	50 ft <sup>2</sup> /ton

### FOND DU LAC RUSTIC LEDGESTONE

#### DIMENSIONS

<b>US: inches (average)</b>	<b>METRIC: mm (average)</b>
l: 4" to 16" (8")	l: 102 to 406 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3" to 5" (4")	w: 76 to 127 (101)

#### TYPICAL BLEND

up to 30 percent may be sawn top and bottom with a bedface face;  
face of stone cannot have a sawn finish

#### TYPICAL PIECE

ends random;  
natural cleft top and bottom;  
weatheredge and seamface face;  
sides natural split or seamface;  
back sawn; stone is linear

## PART NUMBERS

### FULL VENEER

part number: 1BSTBUE02033TN

### THIN VENEER

qty bx flat: 1BTVBUE02035QB  
sm bx flat: 1BTVBUE02035BX  
qty bx corner: 1BTVBUE02537QB  
sm bx corner: 1BTVBUE02536BX

## THIN VENEER

### COMMON COVERAGE PER BOX <sup>\*Est.(can vary)</sup>

Drystack Joint	Standard Joint
8 & 100 square feet	10 & 110 ft <sup>2</sup>

note: packaged for drystack install (8 & 100 ft<sup>2</sup>)

### FOND DU LAC RUSTIC LEDGESTONE

#### DIMENSIONS

<b>US: inches (average)</b>	<b>METRIC: mm (average)</b>
l: 4" to 16" (8")	l: 102 to 406 (203)
h: 3/4" to 2-1/4"	h: 19 to 57
w: 3/4" to 1-1/4" (1")	w: 19 to 31 (25)
corner return 3" to 5" cr: 76 to 127	

#### TYPICAL BLEND

up to 30 percent may be sawn top and bottom with a bedface face;  
face of stone cannot have a sawn finish

#### TYPICAL PIECE

ends random;  
natural cleft top and bottom;  
weatheredge and seamface face;  
sides natural split or seamface;  
back sawn; stone is linear

## ASTM TESTING DATA

FOND DU LAC C97 water absorption—0.36%  
FOND DU LAC C97 density—174.2 pcf  
FOND DU LAC C99  
modulus of rupture—1,470 psi  
FOND DU LAC C170  
compressive strength w/rift—29,040 psi  
compressive strength across rift—34,240 psi  
FOND DU LAC C880  
flexural strength—1,740 psi



www.buechelstone.com