



CASTLE ROCK
JUTE CLOTH
CASTLE ROCK

GEOLOGY: limestone

BASIC USE

exterior walls of buildings and fireplaces
stone shall be mortared in

COLOR RANGE

browns, tans, chocolates, grays, charcoals,
and whites

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) x 170
= approx 170 pounds per cubic foot

PALLET

FULL VENEER: 4,000 pounds
THIN VENEER: 10-15 lbs/ft²; Qty Bx or Sm Bx
Qty Bx - 100 sq ft flats and 50 lineal ft corners
Sm Bx - (24) 8 sq ft flats (192 sq ft) and
(20) 8 lineal ft corners (160 lineal ft)

FULL VENEER

COMMON COVERAGE *Est.(can vary)

Standard Joint	Drystack	Overgrout
40 square feet / ton	30 ft ² /ton	50 ft ² /ton

JUTE CLOTH CASTLE ROCK

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 6" to 42" (14") l: 152 to 1066 (406)

h: 4" to 12" h: 101 to 305

w: 3" to 5" (4") w: 76 to 127 (101)

stone shall not vary in height more than 1/2
an inch in a 12 inch span

EXAMPLE

a stone that is 24 inches long could have a
height of 6 inches on one end and 5 inches
on the other end and be acceptable

TYPICAL PIECE

ends square;
split top, bottom, and sides;
bedface face and back;
stone is squares and rectangles

PART NUMBERS

FULL VENEER

part number: 1BSTKNS03008TN

THIN VENEER

qty bx flat: 1BTVKNS03008QB

sm bx flat: 1BTVKNS03008BX

qty bx corner: 1BTVKNS03508QB

sm bx corner: 1BTVKNS03508BX

THIN VENEER

COMMON COVERAGE PER BOX *Est.(can vary)

Standard Joint	Drystack	Overgrout
8 & 100 square feet	6 & 75 ft ²	10 & 110 ft ²

JUTE CLOTH CASTLE ROCK

DIMENSIONS

US: inches (average) **METRIC: mm (average)**

l: 6" to 24" (12") l: 152 to 533 (304)

h: 4" to 12" h: 101 to 304

w: 3/4" to 1-1/4" (1") w: 19 to 31 (25)

corner return 3" to 5" cr: 76 to 127
stone shall not vary in height more than 1/2
an inch in a 12 inch span

EXAMPLE

a stone that is 24 inches long could have a
height of 6 inches on one end and 5 inches
on the other end and be acceptable

TYPICAL PIECE

ends square;
split top, bottom, and sides;
bedface face and sawn back;
stone is squares and rectangles

ASTM TESTING DATA

JUTE CLOTH C97 water absorption—10.03%

specific gravity — 1.995 to 2.008

density—125.1 lbs/ft³

JUTE CLOTH C170

dry perpendicular—4,040 psi

wet perpendicular—1,830 psi

dry parallel —3,210 psi

wet parallel—1,480 psi

JUTE CLOTH C880

flexural strength -wet —440 psi

flexural strength -dry —600 psi



www.buechelstone.com