

WALL STONE

SILVERDALE SAWN WALL STONE



GEOLOGY: limestone

BASIC USE

for retaining ground;
stone is typically dryset (no mortar used)
when installed

COLOR RANGE

yellows and creams to slight buffs with occa-
sional veining

COLOR CONSISTENCY PER PALLET

consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 160
= approx 134 pounds per cubic foot

PALLET

3,000 - 4,000 pounds

SAWN WALL STONE

COMMON COVERAGE *Est.(can vary)

8 inch
20 ft²/ton

SILVERDALE WALL STONE

4" DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 6" to 42" (16")	l: 152 to 1066 (406)
h: 4"	h: 101
w: 7"- 9" (8")	w: 117 to 228

6" DIMENSIONS

US: inches (average)	METRIC: mm (average)
l: 6" to 42" (16")	l: 152 to 1066 (406)
h: 6"	h: 152

note: +/- 1/4" on height

note: sides of stone shall be no less than 2 1/2"
(63 mm) in width

TYPICAL PIECE

ends square; sawn top and bottom, split
sides, face and back;
stone is mostly rectangular



PART NUMBERS

part number 8" (4") : 1RWSKNS01001TN

part number 8" (6") : 1RWSKNS01003TN

ASTM TESTING DATA

SILVERDALE C97 water absorption—7.27%

SILVERDALE C97 density—134.1 pcf

SILVERDALE C97 specific gravity—2.149

SILVERDALE C99

modulus of rupture—1,174 psi

SILVERDALE C170

compressive strength —6,631 psi

SILVERDALE C241

abrasion resistance—5.38



www.buechelstone.com