



## STEPS

### WHITE MARIGOLD SAWN STEPS



**GEOLOGY:** limestone

#### BASIC USE

for steps

#### COLOR RANGE

light grays to buffs with occasional blue veins

#### COLOR CONSISTENCY PER PALLET

consistent

#### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 125.1$   
= approx 125.1 pounds per cubic foot

#### PALLET

2,000 to 3,000 pounds

#### STEPS PER PALLET

18" x 36" = 8 steps per pallet

18" x 48" = 6 steps per pallet

24" x 36" = 5 steps per pallet

24" x 48" = 5 steps per pallet

## SAWN STEPS

### WHITE MARIGOLD 18"x36" SAWN

#### STEPS

##### DIMENSIONS

US: inches

l: 35" to 37"

h: 6"

w: 17" to 19"

note: sawn to 6" height

note:  $\pm 1/4"$  on height

METRIC: mm

l: 889 to 940 mm

h: 152 mm

w: 431 to 482 mm

### WHITE MARIGOLD 18"x48" SAWN

#### STEPS

##### DIMENSIONS

US: inches

l: 47" to 49"

h: 6"

w: 17" to 19"

note: sawn to 6" height

note:  $\pm 1/4"$  on height

METRIC: mm

l: 1194 to 1244 mm

h: 152 mm

w: 431 to 482 mm

##### TYPICAL PIECE

ends square;

sawn top and bottom;

split sides, face and back;

stone is rectangular;

custom sizing by request

## PART NUMBERS

part number 18"x36": 1STEKNS04001EA

part number 24"x36": 1STEKNS04003EA

part number 18"x48": 1STEKNS04002EA

part number 24"x48": 1STEKNS04004EA

## SAWN STEPS

### WHITE MARIGOLD 24"x36" SAWN

#### STEPS

##### DIMENSIONS

US: inches

l: 35" to 37"

h: 6"

w: 23" to 25"

note: sawn to 6" height

note:  $\pm 1/4"$  on height

METRIC: mm

l: 889 to 940 mm

h: 152 mm

w: 584 to 635 mm

### WHITE MARIGOLD 24"x48" SAWN

#### STEPS

##### DIMENSIONS

US: inches

l: 47" to 49"

h: 6"

w: 23" to 25"

note: sawn to 6" height

note:  $\pm 1/4"$  on height

METRIC: mm

l: 1194 to 1244 mm

h: 152 mm

w: 584 to 635 mm

##### TYPICAL PIECE

ends square;

sawn top and bottom;

split sides, face and back;

stone is rectangular;

custom sizing by request

## ASTM TESTING DATA

**WHITE MARIGOLD C97** water

absorption—9.43%

specific gravity — 2.042 to 2.066

density—125.1 lbs/ft<sup>3</sup>

**WHITE MARIGOLD C170**

dry perpendicular—5,490 psi

wet perpendicular—3,680 psi

dry parallel —4,530 psi

wet parallel—3,420 psi

**WHITE MARIGOLD C880**

flexural strength -wet —500 psi

flexural strength -dry —700 psi

**WHITE MARIGOLD C1353**

abrasion—3.5

**WHITE MARIGOLD ANSI A326.3**

friction—0.83



www.buechelstone.com