



WALL STONE
WHITE MARIGOLD
SAWN
WALL STONE

GEOLOGY: limestone

BASIC USE

for retaining ground;
 stone is typically dryset (no mortar used)
 when installed

COLOR RANGE

yellows and creams to slight buffs

COLOR CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 125.1
 = approx 125.1 pounds per cubic foot

PALLET

3,000 - 4,000 pounds

PART NUMBERS

part number 8" (4") : 1RWSKNS04001TN

part number 8" (6") : 1RWSKNS04003TN

SNAPPED WALL STONE

COMMON COVERAGE *Est.(can vary)

8 inch

20 square feet / ton

WHITE MARIGOLD WALL STONE

4" DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 6" to 42" (16") l: 152 to 1066 (406)

h: 4" h: 101

w: 7"-9" (8") w: 117 to 228

6" DIMENSIONS

US: inches (average) METRIC: mm (average)

l: 6" to 42" (16") l: 152 to 1066 (406)

h: 6" h: 152

note: +/- 1/4" on the height note: sides of
 stone shall be no less than 2 1/2" (63 mm) in
 width

WHITE MARIGOLD WALL STONE

TYPICAL PIECE

ends square;
 natural cleft top and bottom;
 split sides, face, and back;
 stone is mostly rectangular

ASTM TESTING DATA

WHITE MARIGOLD C97 water
 absorption—9.43%
 specific gravity — 2.042 to 2.066
 density—125.1 lbs/ft³

WHITE MARIGOLD C170
 dry perpendicular—5,490 psi
 wet perpendicular—3,680 psi
 dry parallel—4,530 psi
 wet parallel—3,420 psi

WHITE MARIGOLD C880
 flexural strength -wet —500 psi
 flexural strength -dry —700 psi

WHITE MARIGOLD C1353
 abrasion—3.5

WHITE MARIGOLD ANSI A326.3
 friction—0.83

